

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MAROOTA NSW 2756

Job No 7018/1
Date: 06/04/2020
Tested By: SS
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Super Fine SAND	
Sieve Analysis		
Laboratory Number	7018/1-1653	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	Moisture Content % AS1289 2.1.1
4.75mm	100	
2.36mm	100	6.3
1.18mm	100	
600 microns	99	% Clay & Fine Silt (Settling Method)
300 microns	85	
150 microns	43	
75 microns	13.5	
Date Sampled	01/04/2020	N/D
Sampling Procedure	Sampled by Client. Results apply to sample as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

06/04/2020



34 Borec Road, Penrith NSW 2750
Telephone: (02) 4722 2744

Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111

email: info@geotech.com.au www.geotech.com.au