

Client: P F FORMATION
 1774 WISEMANS FERRY ROAD
 MAROOTA NSW 2756

Job No: 7018/1
 Date Tested: 23/09/2020
 Tested By: BN
 Checked By: AK

Project: MATERIAL ASSESSMENT
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Type B Compaction SAND	
Sieve Analysis		
Laboratory Number	7018/1-1725	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	Moisture Content % AS1289 2.1.1
4.75mm	99	
2.36mm	95	7.5
1.18mm	92	
600 microns	71	% Clay & Fine Silt (Settling Method)
300 microns	24	
150 microns	4	Not Determined
75 microns	0.5	
Date Sampled	14/09/2020	
Sampling Procedure	Sampled by Client. Results apply to sample as received.	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench 29/09/2020

Approved Signatory

