

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MAROOTA NSW 2756

Job No 7018/1
Date: 26/09/2017
Tested By: DS
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12	
Material Description	Bricklaying SAND - (White)
Sieve Analysis	
Laboratory Number	7018/1-1183
<u>Sieve Size</u>	Percentage Passing
9.5mm	100
4.75mm	100 0.2
2.36mm	96
1.18mm	82
600 microns	36
300 microns	8
150 microns	1
75 microns	10.5
Date Sampled	1/09/2017
Sampling Procedure	Sampled by Client
Sampling Location	Ex Maroota Quarry

Form No: R024 Version 05 06/13 - issued by ER



Accredited for compliance with ISO/IEC 17025.

A Kench 26/09/2017
Approved Signatory

Nata Accreditation Number 2734
Corporate Site Number 2727



Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200