

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MARROOTA NSW 2756

Job No 7018/1
Date: 08/06/2018
Tested By: DS
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

Page 1 of 1

| TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 | |
|--|-----------------------------|
| Material Description | Bricklaying SAND - (Yellow) |
| Sieve Analysis | |
| Laboratory Number | 7018/1-1404 |
| <u>Sieve Size</u> | Percentage Passing |
| 9.5mm | 100 |
| 4.75mm | 100 |
| 2.36mm | 93 |
| 1.18mm | 84 |
| 600 microns | 52 |
| 300 microns | 12 |
| 150 microns | 2 |
| 75 microns | 12.1 |
| Date Sampled | 04/06/2018 |
| Sampling Procedure | Sampled by Client |
| Sampling Location | Ex Maroota Quarry |

Form No: R024 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench 12/06/2018
Approved Signatory



Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200