

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MAROOKA NSW 2756

Job No 7018/1
Date: 10/08/2020
Tested By: SS
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12	
Material Description	Bricklaying SAND - (Yellow)
Sieve Analysis	
Laboratory Number	7018/1-1706
<u>Sieve Size</u>	<u>Percentage Passing</u>
9.5mm	100
4.75mm	100 0.2
2.36mm	95
1.18mm	89
600 microns	54
300 microns	17
150 microns	4
75 microns	11.7
Date Sampled	27/07/2020
Sampling Procedure	Sampled by Client. Results apply to sample as received
Sampling Location	Ex Maroota Quarry

Form No: R024 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench 10/08/2020
Approved Signatory



Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au