

Client: P F FORMATION
 1774 WISEMANS FERRY ROAD
 MAROOTA NSW 2756

Job No: 7018/1
 Date Tested: 16/03/2021
 Tested By: JC
 Checked By: HW

Project: MATERIAL ASSESSMENT
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Super Fine SAND	
Sieve Analysis		
Laboratory Number	7018/1-1781	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	<div style="border: 1px solid black; padding: 5px; text-align: center;"> Moisture Content % AS1289 2.1.1 </div>
4.75mm	100	
2.36mm	100	<div style="border: 1px solid black; padding: 5px; text-align: center; font-size: 1.2em;"> 6.7 </div>
1.18mm	100	
600 microns	99	<div style="border: 1px solid black; padding: 5px; text-align: center;"> % Clay & Fine Silt (Settling Method) </div>
300 microns	84	
150 microns	46	
75 microns	16.0	
Date Sampled	01/03/2021	<div style="border: 1px solid black; padding: 5px; text-align: center;"> Not Determined </div>
Sampling Procedure	Sampled by Client. Results apply to sample as received.	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

16/03/2021

Approved Signatory

