

Client: P F FORMATION
 1774 WISEMANS FERRY ROAD
 MAROOTA NSW 2756

Job No: 7018/1
 Date Tested: 06/09/2021
 Tested By: BC
 Checked By: AK

Project: MATERIAL ASSESSMENT
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Compaction SAND Type A	
Sieve Analysis		
Laboratory Number	7018/1-1843	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	Moisture Content % AS1289 2.1.1
4.75mm	99	
2.36mm	90	3.7
1.18mm	74	
600 microns	51	% Clay & Fine Silt (Settling Method)
300 microns	20	
150 microns	5	
75 microns	0.7	
Date Sampled	31/08/2021	N/A
Sampling Procedure	Sampled by Client. Results apply to sample as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

07/09/2021



34 Borec Road, Penrith NSW 2750
 Telephone: (02) 4722 2744

Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
 Telephone: (02) 9607 6111

email: info@geotech.com.au www.geotech.com.au