

Client: P F FORMATION  
 1774 WISEMANS FERRY ROAD  
 MAROOTA NSW 2756

Job No: 7018/1  
 Date Tested: 08/02/2022  
 Tested By: NP  
 Checked By: AK

Project: MATERIAL ASSESSMENT  
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

## TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Coarse SAND	
Sieve Analysis		
Laboratory Number	7018/1-1903	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	Moisture Content % AS1289 2.1.1
4.75mm	99	
2.36mm	90	2.2
1.18mm	74	
600 microns	54	% Clay & Fine Silt (Settling Method)
300 microns	25	
150 microns	6	
75 microns	1.3	
Date Sampled	31/01/2022	5.7
Sampling Procedure	Sampled by Client. Results apply to sample as received	
Sampling Location	Emu Plains Depot	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

11/02/2022

