

Client: P F FORMATION
 1774 WISEMANS FERRY ROAD
 MAROOTA NSW 2756

Job No 7018/1
 Date Tested: 21/11/2022
 Tested By: JC
 Checked By: AK

Project: MATERIAL ASSESSMENT
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Type B Compaction SAND	
Sieve Analysis		
Laboratory Number	7018/1-1965	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	Moisture Content % AS1289 2.1.1
4.75mm	98	
2.36mm	93	6.0
1.18mm	88	
600 microns	75	% Clay & Fine Silt (Settling Method)
300 microns	32	
150 microns	7	
75 microns	1.1	
Date Sampled	09/11/2022	N/A
Sampling Procedure	Sampled by Client. Results apply to sample as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

28/11/2022

