

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MAROOTA NSW 2756

Job No 7018/1
Date Tested: 21/11/2022
Tested By: JC
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

| TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 | |
|--|--|
| Material Description | Bricklaying SAND - (White) |
| Sieve Analysis | |
| Laboratory Number | 7018/1-1968 |
| <u>Sieve Size</u> | <u>Percentage Passing</u> |
| 9.5mm | 100 |
| 4.75mm | 100 0.1 |
| 2.36mm | 97 |
| 1.18mm | 91 |
| 600 microns | 45 |
| 300 microns | 9 |
| 150 microns | 2 |
| 75 microns | 12.5 |
| Date Sampled | 10/11/2022 |
| Sampling Procedure | Sampled by Client. Results apply to sample as received |
| Sampling Location | Ex Maroota Quarry |

Form No: R024 Version 05 06/13 - issued by ER



Accredited for compliance with ISO/IEC 17025.

A Kench 28/11/2022
Approved Signatory

Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

