

Client: P F FORMATION
 1774 WISEMANS FERRY ROAD
 MAROOKA NSW 2756

Job No 7018/1
 Date Tested: 12/05/2023
 Tested By: TS
 Checked By: AK

Project: MATERIAL ASSESSMENT
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33		
Material Description	Coarse SAND	
Sieve Analysis		
Laboratory Number	7018/1-1994	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	<div style="border: 1px solid black; padding: 5px; text-align: center;"> Moisture Content % AS1289 2.1.1 </div>
4.75mm	99	
2.36mm	93	3.5
1.18mm	79	<div style="border: 1px solid black; padding: 5px; text-align: center;"> % Clay & Fine Silt (Settling Method) </div>
600 microns	56	
300 microns	21	
150 microns	4	
75 microns	0.5	4.8
Date Sampled	17/04/2023	
Sampling Procedure	Sampled by Client. Results apply to sample as received	
Sampling Location	Emu Plains Depot	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

15/05/2023

