

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MAROOTA NSW 2756

Job No 7018/1
Date Tested: 19/10/2023
Tested By: TS
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33	
Material Description	Type A Compaction SAND
Sieve Analysis	
Laboratory Number	7018/1-2030
<u>Sieve Size</u>	Percentage Passing
	Pre-treatment Nil - Standard Oven Drying
9.5mm	100
4.75mm	99 1.4
2.36mm	92
1.18mm	81
600 microns	63
300 microns	26
150 microns	5
75 microns	0.8
Date Sampled	12/10/2023
Sampling Procedure	Sampled by Client. Results apply to sample as received
Sampling Location	Emu Plains Depot

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

25/10/2023



34 Borec Road, Penrith NSW 2750
Telephone: (02) 4722 2744

Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111

email: info@geotech.com.au www.geotech.com.au