

Client: P F FORMATION
 1774 WISEMANS FERRY ROAD
 MAROOKA NSW 2756

Job No 7018/1
 Date Tested: 07/12/2023
 Tested By: TS
 Checked By: AK

Project: MATERIAL ASSESSMENT
 QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 & 33			
Material Description	Compactin SAND Type B (Sydney Water - Grade B)		
Sieve Analysis			
Laboratory Number	7018/1-2038		
Sieve Size	Percentage Passing	Specification	Pre-treatment Nil - Standard Oven Drying
9.5mm	100		
4.75mm	100	0.0	
2.36mm	99	100 - 90	
1.18mm	97	85 - 100	
600 microns	91	70 - 100	
300 microns	59	50 - 100	
150 microns	8	0 - 40	
75 microns	1.0	0 - 5	
Date Sampled	30/11/2023		
Sampling Procedure	Sampled by Client. Results apply to sample as received		
Sampling Location	Emu Plains Depot		

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

11/12/2023

