

Client: P F FORMATION
1774 WISEMANS FERRY ROAD
MAROOKA NSW 2756

Job No 7018/1
Date Tested: 30/04/2024
Tested By: JF
Checked By: AK

Project: MATERIAL ASSESSMENT
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12	
Material Description	Bricklaying SAND - (White)
Sieve Analysis	
Laboratory Number	7018/1-2048
<u>Sieve Size</u>	<u>Percentage Passing</u>
9.5mm	100
4.75mm	100 0.0
2.36mm	97
1.18mm	92
600 microns	69
300 microns	17
150 microns	1
75 microns	10.5
Date Sampled	March 2024
Sampling Procedure	Sampled by Client. Results apply to sample as received
Sampling Location	Ex Maroota Quarry

Form No: R024 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench 01/05/2024
Approved Signatory



Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200