

Client: P F FORMATION  
1774 WISEMANS FERRY ROAD  
MAROOTA NSW 2756

Job No 7018/1  
Date Tested: 05/06/2024  
Tested By: TS  
Checked By: AK

Project: MATERIAL ASSESSMENT  
QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

## TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12	
Material Description	Bricklaying SAND - (Yellow)
Sieve Analysis	
Laboratory Number	7018/1-2070
<u>Sieve Size</u>	Percentage Passing
9.5mm	100
4.75mm	100 0.5
2.36mm	92
1.18mm	80
600 microns	57
300 microns	25
150 microns	3
75 microns	12.5
Date Sampled	23/05/2024
Sampling Procedure	Sampled by Client. Results apply to sample as received
Sampling Location	Ex Maroota Quarry

Form No: R024 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench 06/06/2024  
Approved Signatory



Head Office:  
34 Borec Road, Penrith NSW 2750  
P O Box 880 Penrith NSW 2751  
Telephone: (02) 4722 2744

Prestons Laboratory:  
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
Telephone: (02) 9607 6111