

- Client: P F FORMATION 1774 WISEMANS FERRY ROAD MAROOTA NSW 2756
- Project: MATERIAL ASSESSMENT QUARRY SAMPLE TESTING, EMU PLAINS DEPOT

## **TEST RESULTS**



Job No 70<sup>4</sup> Date Tested: 05/ Tested By: TS Checked By: AK

7018/1 05/06/2024 TS AK

laterial Description	Fine SAND			
Sieve Analysis				
Laboratory Number	7018/1-2068			
<u>Sieve Size</u>	Percentage Passing		Pre-treatment Nil - Standard Oven Drying	
9.5mm	100		Moisture Content % AS1289 2.1.1	
4.75mm	100	0.0		
2.36mm	100		4.6	
1.18mm	98			
600 microns	93			
300 microns	36		% Clay & Fine Silt (Settling Method)	
150 microns	2			
75 microns	0.1		4.0	
Date Sampled	27/05/2024		10	
Sampling Procedure	Sampled by Client. Results a	pply to sample as received		
Sampling Location m No: R 025 Version 05 06/13 - issue	Ex Maroota Quarry			



Corporate Site Number 2727

34 Borec Road, Penrith NSW 2750 Telephone: (02) 4722 2744

Unit 4, 18-20 Whyalla Place, Prestons NSW 2170 Telephone: (02) 9607 6111

email: info@geotech.com.au www.geotech.com.au