

Material Test Report

Report Number: 9810-1
Issue Number: 1
Date Issued: 17/02/2025
Client: P F FORMATION
 1774 WISEMANS FERRY ROAD, MAROOKA NSW 2756
Project Number: 9810
Project Name:
Project Location: 1 Patricia Fay Drive Maroota, NSW 2765
Work Request: 311
Sample Number: S-311C
Date Sampled: 29/01/2025
Dates Tested: 13/02/2025 - 14/02/2025
Sampling Method: Sampled by Client
The results apply to the sample as received
Preparation Method: AS 1289.1.1 - Sampling and Preparation of Soils
Sample Location: Yellow Bricklaying Sand
Material: Yellow Bricklaying Sand

GEOTECH

TESTING PTY LTD
 ABN 71 076 676 321

Geotech Testing Pty Ltd
 Penrith Laboratory
 34 Borec Road Penrith NSW 2750
 Phone: (02) 4722 2744
 Email: matthew@geotech.com.au

Accredited for compliance with ISO/IEC 17025 - Testing



Approved Signatory: Mathew Morley
 Laboratory Manager
 NATA Accredited Laboratory Number: 2734

Particle Size Distribution (AS1141.11.1)		
Sample Washing	Sample was Washed	
Sieve	Passed %	Passing Limits
75 mm	100	
63 mm	100	
53 mm	100	
37.5 mm	100	
26.5 mm	100	
19 mm	100	
13.2 mm	100	
9.5 mm	100	
6.7 mm	100	
4.75 mm	100	
2.36 mm	97	
1.18 mm	93	
0.6 mm	81	
0.425 mm	63	
0.3 mm	42	
0.15 mm	20	
0.075 mm	11	

